

1. Application Sector

DAMTEC® rubber is a floor underlay for footfall sound reduction and thermal insulation; used in building construction and renovation, specially in wet rooms under ceramic tiles.

2. Material

Fine granules of recycled rubber with PU elastomer bonding agent

3. Appearance

colour: black
surface: fine granular texture

4. Dimensions/Tolerances

width:	1,000 mm	± 1.5 %
length:	on request	± 1.5 %
available thickness:	3, 4, 5 and 6 mm	± 0.3 mm
density:	approx. 800 kg/m ³	

The data sheet is not subject to any change service! All information is without guarantee.
With the publication of this product data sheet all former issues cease to be valid.

Seite 1 von 2

5. Physical Characteristics

tensile strength:	approx. 0.6 N/mm ²	(ISO 1798)
elongation at break:	approx. 60%	(ISO 1798)
service temperature range:	- 30°C to 80°C	
flammability rating:	B 2	(DIN 4102-1)
heat transmission coefficient:	0.03 m ² K/W for 3 mm slab	(DIN 52612)
impact sound improvement:	$\Delta L_w = 20\text{dB}$ without covering	
	$\Delta L_w = 17\text{dB}$ under 8 mm tiles	(ISO 140-8/ISO 717-2)

6. Installation:

Installation is to be carried out in accordance with the **DAMTEC® rubber** installation instructions.

7. Other Matters:

Castor chair behaviour and residual indentation after static loading of the flooring can change in accordance with the insulating underlay used. Only use underlay approved by the floor manufacturer.

Prior to any installation work, carefully read and observe the usage instructions and processing guidelines of the adhesive cement and floor finish manufacturers. In case of doubt, please contact the manufacturer's applications engineering department for advice.

DISCLAIMER:

The information provided is intended only as a summary and general overview on matters of interest. The information is not intended to be comprehensive nor does it constitute expert advice. KRAIBURG RELASTEC shall not be liable for incidental and/or consequential damages directly or indirectly sustained, nor any loss caused by not complying with relevant industry/product standards and improper use of any Damtec® products. Due to varying construction methods, any other circumstances not stated above should be brought to the attention of KRAIBURG RELASTEC for review. For suitability to the prevailing site conditions, it is advised that certified testing should be conducted. It is recommended to seek further advice on your application with our technical staff prior to use.

The data sheet is not subject to any change service! All information is without guarantee.
With the publication of this product data sheet all former issues cease to be valid.

Seite 2 von 2